Scotch[®] Strapping Tape 8898

Product Description	Scotch [®] Strapping Tape 8898 is a general-purpose tape with a tensilized polypropylene film backing and pressure-sensitive synthetic adhesive. The tape is designed for a wide variety of industrial and packaging applications. Some typical applications include bundling, reinforcing, strapping, box closing, and appliance securing. The backing provides proper stiffness and excellent abrasion, moisture, and scuff resistance. The pressure-sensitive adhesive is specifically formulated to provide balanced adhesion to most fiberboard surfaces and a wide variety of plastic and metal surfaces. We suggest tests be completed to determine suitability particularly on surfaces other than those previously mentioned.		
Construction	Backing	Adhesive	Colors
	Tensilized polypropylene	Pressure-sensitive synthetic rubber resin	Blue, ivory
Typical Dhysical	Note: The following to	physical information and data should be considered	rad ranrasantativ
		chnical information and data should be conside nd should not be used for specification purpose	
	or typical only, a	nd should not be used for specification purpose 75 oz./in. width (82 N/100 mm width)	s. ASTM Test Metho D-3330
	or typical only, a Adhesion to Steel: Tensile Strength:	nd should not be used for specification purpose 75 oz./in. width (82 N/100 mm width) 160 lbs./in.width (2800 N/100 mm width)	s. ASTM Test Metho D-3330 D-3759
Typical Physical Properties	or typical only, a Adhesion to Steel: Tensile Strength: Elongation at Break:	nd should not be used for specification purpose 75 oz./in. width (82 N/100 mm width) 160 lbs./in.width (2800 N/100 mm width) 32%	s. ASTM Test Metho D-3330 D-3759 D-3759
	or typical only, a Adhesion to Steel: Tensile Strength:	nd should not be used for specification purpose 75 oz./in. width (82 N/100 mm width) 160 lbs./in.width (2800 N/100 mm width)	s. ASTM Test Metho D-3330 D-3759
Properties	or typical only, a Adhesion to Steel: Tensile Strength: Elongation at Break:	nd should not be used for specification purpose 75 oz./in. width (82 N/100 mm width) 160 lbs./in.width (2800 N/100 mm width) 32%	s. ASTM Test Metho D-3330 D-3759 D-3759 D-3652
Properties	or typical only, a Adhesion to Steel: Tensile Strength: Elongation at Break: Tape Thickness:	nd should not be used for specification purpose 75 oz./in. width (82 N/100 mm width) 160 lbs./in.width (2800 N/100 mm width) 32% 4.6 mil (0.12 mm) .47 in. (12 mm), .71 in. (18 mm), .94	s. ASTM Test Metho D-3330 D-3759 D-3759 D-3652
	or typical only, a Adhesion to Steel: Tensile Strength: Elongation at Break: Tape Thickness:	nd should not be used for specification purpose 75 oz./in. width (82 N/100 mm width) 160 lbs./in.width (2800 N/100 mm width) 32% 4.6 mil (0.12 mm) .47 in. (12 mm), .71 in. (18 mm), .94 1.9 in. (48 mm) and 2.8 in. (72	s. ASTM Test Metho D-3330 D-3759 D-3759 D-3652 in. (24 mm), mm)

Storage Conditions

Store behind present stock. Store in a clean, dry place. Temperature of 40-80°F (4-26°C) and 40-50% relative humidity are recommended. Rotate your stock.

Scotch® Strapping Tape

8898

For Additional Information	To request additional product information or to arrange for sales assistance, call toll free 1-800-362-3550 or visit www.3M.com/packaging. Address correspondence to: 3M Industrial Adhesives and Tapes Division, Building 21-1W-10, 900 Bush Avenue, St. Paul, MN 55144-1000. Our fax number is 651-778-4244. In Canada, phone: 1-800-364-3577. In Puerto Rico, phone: 1-787-750-3000. In Mexico, phone: 52-70-04-00.
Important Notice	3M MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. User is responsible for determining whether the 3M product is fit for a particular purpose and suitable for user's application. Please remember that many factors can affect the use and performance of a 3M product in a particular application. The materials to be bonded with the product, the surface preparation of those materials, the product selected for use, the conditions in which the product is used, and the time and environmental conditions in which the product is expected to perform are among the many factors that can affect the use and performance of a 3M product. Given the variety of factors that can affect the use and performance of a 3M product, some of which are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's application.
Limitation of Remedies and Liability	If the 3M product is proved to be defective, THE EXCLUSIVE REMEDY, AT 3M'S OPTION, SHALL BE TO REFUND THE PURCHASE PRICE OF OR TO REPAIR OR REPLACE THE DEFECTIVE 3M PRODUCT. 3M shall not otherwise be liable for loss or damages, whether direct, indirect, special, incidental, or consequential, regardless of the legal theory asserted, including, but not limited to, contract, negligence, warranty, or strict liability.



Industrial Business Industrial Adhesives and Tapes Division 3M Center, Building 21-1W-10, 900 Bush Avenue St. Paul, MN 55144-1000



Recycled Paper 40% pre-consumer 10% post-consumer